

# Technical Data Sheet



**Product name: ReForm™ - rTitan**

**Date of issue: 2 May 2017**

**Version: v1**

ReForm is a sustainable initiative within Formfutura to efficiently manage residual extrusion waste streams and re-use them into high-end upcycled filaments. The ideology behind ReForm is to make 3D printing more sustainable – without having to make compromises on material properties – and yet keep it affordable.

ReForm rTitan is based on exactly the same unique formulation as our TitanX filament range, but is made out of residual extrusion waste streams which are re-compounded and homogenized into a high-end and FDM/FFF-optimized upcycled TitanX-based filament with significantly less environmental impact.

Properties	Typical value	Test Method	Test condition
<b>Physical</b>			
Specific gravity	1.10 g/cc	ISO 1183	-
Melt flow rate	41 g/10min	ISO 1133	260° C/5Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
<b>Mechanical</b>			
Impact strength	58 KJ/m <sup>2</sup>	ISO 179	Charpy Notched @23° C (73° F)
Tensile strength	43.6 Mpa	ISO 527	@Yield 50mm/min (2 inch/min)
Tensile modulus	2030 Mpa	ISO 527	1mm/min
Elongation at break	34%	ISO 527	@ Break 50mm/min (2 inch/min)
Flexural strength	-	-	-
Flexural modulus	-	-	-
Hardness	-	-	-
<b>Thermal</b>			
Print temperature	± 240 - 260° C	-	-
Melting temperature	± 235 ± 10° C	ISO 294	-
Viscat softening temp.	± 97° C	ISO 306	VST/A/50 (50° C/h, 10N)
<b>Optical</b>			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance		Diameter	Tolerance	Roundness
HS Code	39169090	1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes			
FDA compliant	Yes			

Formfutura VOF	CoC: 55502105	Tel: +31 (0)85 002 0881
Groenestraat 215	VAT: NL851741083B01	Email: info@formfutura.com
6531 HH Nijmegen	EORI: NL851741083	Website: www.formfutura.com
The Netherlands		

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the forementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.